

Shinichi OKADA, et al.

(§371 of International Application PCT/JP04/11195)

IN THE SPECIFICATION:

Please replace Table 1 beginning at page 46 and bridging to page 47 with the following rewritten table:

Table 1

	Example 1	Example 2	Example 3	Example 4
Resin	A	B	C	D
Amount of resin	750	750	1000	750
FASTOGEN SUPERMAGENTA RTS	4630	4630	4750	4630
Phthalimidomethylated 3,10-dichloroquinacridone	380	380	250	380
Quinacridonsulfonic acid-based compound				
Diethylene glycol	2700	2900	3200	3100
Aqueous 34% by mass potassium hydroxide solution	333	335	489	322
Ion-exchanged water	200			
Additional ion-exchanged water for kneading	400	800	300	300
Additional ion-exchanged water for dilution	6400	6200	6700	6700
Solid content of colored kneaded mixture after dilution	39%	39.9%	38.5%	38.1%
Colored kneaded mixture after dilution	12000	12000	12000	12000
Diethylene glycol	5830	5810	1350	1490
Ion-exchanged water	5570	6150	9750	9340
Water-based pigment dispersion before dispersion treatment	A-1	B-1	C-1	D-1
Supply flow rate of dispersion to disperser	200 g/10 sec	185 g/10 sec	190 g/10 sec	195 g/10 sec
Content of pigment of water-based pigment dispersion	15.8%	15.8%	15.4%	15.8%
Water-based pigment dispersion	A-2	B-2	C-2	D-2

*unit is g unless otherwise so indicated

Table 1 (continued)

	Comparative Example 1	Comparative Example 3	Comparative Example 4	Comparative Example 5
Resin	B	E	F	G
Amount of resin	1000	750	750	750
FASTOGEN SUPERMAGENTA RTS	5000	4630	4630	4630
Phthalimidomethylated 3,10-dichloroquinacridone		380	380	380
Quinacridonsulfonic acid-based compound				
Diethylene glycol	3200	2500	3300	3000
Aqueous 34% by mass potassium hydroxide solution	447	331	338	329
Ion-exchanged water			200	
Additional ion-exchanged water for kneading	200	200	400	500
Additional ion-exchanged water for dilution	6000	6800	6400	6500
Solid content of colored kneaded mixture after dilution	40.4%	39%	38.4%	39.2%
Colored kneaded mixture after dilution	12000	12000	12000	12000
Diethylene glycol	1420	2000	1340	1610
Ion-exchanged water	11250	9400	9700	9910
Water-based pigment dispersion before dispersion treatment	E-1	G-1	H-1	I-1
Supply flow rate of dispersion to disperser	200 g/10 sec	200 g/10 sec	195 g/10 sec	200 g/10 sec
Content of pigment of water-based pigment dispersion	16%	15.8%	15.8%	15.8%
Water-based pigment dispersion	E-2	G-2	H-2	I-2

*unit is g unless otherwise so indicated

Please replace Table 2 beginning at page 55 and bridging to page 56 with the following rewritten table:

Table 2

		Example 5	Example 6	Example 7	Example 8	Example 9
Kneading	Resin	B	B	D	B	D
	Amount of resin	750	750	750	750	750
	FASTOGEN SUPERMAGENTA RTS	4250	4250	4250	4750	4630
	Phthalimidomethylated 3,10-dichloroquinacridone	250	250	250	250	380
	Hydrous cake of quinacridonesulfonic acid-based compound	1742	1746	1746		
	Content of hydrous cake	28.7%	28.6%	28.6%		
	Diethylene glycol	2000	2000	2000	3000	3100
	Aqueous 34% by mass potassium hydroxide solution	335	335	322	335	332
	Additional ion-exchanged water for kneading	400	200		200	300
	Additional diethylene glycol for kneading			200		
Dilution	Additional ion-exchanged water for dilution	5600	6000	6000	6800	6700
	Solid content of colored kneaded mixture after dilution	40.6%	42%	41.2%	39.4%	38.1%

*unit is g unless otherwise so indicated

Table 2 (continued)

		Example 5	Example 6	Example 7	Example 8	Example 9
Dispersion I	Colored kneaded mixture after dilution	12000	12000	12000	12000	12000
	Diethylene glycol	2490	2410	2360	1610	1490
	Ion-exchanged water	9880	10820	10330	10020	9340
	Water-based pigment dispersion before dispersion treatment	J-1	K-1	L-1	M-1	N-1
	Delivery amount of disperser	200 g/10 sec	190 g/10 sec	200 g/10 sec	200 g/10 sec	200 g/10 sec
	Content of pigment of water-based pigment dispersion	14.5%	14.5%	14.5%	16.2%	15.8%
	Water-based pigment dispersion	J-2	K-2	L-2	M-2	N-2
Dispersion II	Water-based pigment dispersion				62.96	66.55
	10% by mass quinacridonesulfonic acid-based compound				12.63	6.38
	Ion-exchanged water				4.41	7.06
	Content of pigment of dispersion after dispersion II				12.8%	13.1%
	Water-based pigment dispersion after dispersion II				M-3	N-3

*unit is g unless otherwise so indicated

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.